

SHANDONG TAIRAN IMPORT AND EXPORT CO.,LTD

Address:NO. 3, Yanhe Road, Boshan, Zibo, Shandong, China
Email:wp@cnjingganrefractory.com/sdwenping@163.com
Contact:Rose Tel/Wechat:+86-13275332819
Tel:86-533-4188518 Fax:86-533-4188518

Gunning Material For Tundish



1,Product description:

The tundish gunning material produced by magnesia sand and olivine sand plus a variety of additives has superior performance. It is a heat hardening or gas hardening refractory with strong adhesion. It can obtain a thicker gunning layer with high density, low rebound rate and good application effect.

2, Technical index

ITEM	Unit	MGP-1	MGP-2
MgO	%	>65	>75
CaO	%	1.5-2.0	2.0-2.5
SIO ₂	%	23-25	17-18
Fe ₂ O ₃	%	≤5.0	≤3.0
Al ₂ O ₃	%	<1.5	<1.4
Density	g/cm ³	≥1.6	≥1.5
Flexural strength	Mpa	≥2.0	≥2.5
High temperature flexural strength	1500°C Mpa	≥5	≥7
Linear change rate	1500°C *3h,%	<-2.0	<-2.0
Thermal conductivity	1000°C,w/m.k	<0.6	<0.5

3,Construction method: spray the mixture onto the gunning surface with a spray gun

4, Features

- 1) The mixture forms slurry after adding water, which is easy to spray onto the gunning surface
- 2) The construction is simple and convenient
- 3) Strong adhesion and low rebound rate
- 4) Corrosion resistance, strong slag corrosion ability and good application effect

SHANDONG TAIRAN IMPORT AND EXPORT CO.,LTD

5) High temperature flexural strength and low temperature linear change rate

6) Strong compactness

5,Application: tundish gunning

6,Storage: the products are packed in waterproof bags. It is strictly prohibited to get wet in rain and snow. The products are stored in a moisture-proof and ventilated warehouse for 3-6 months. If the products are found to be caked due to moisture, they are refused to use.

7,Good feedback of product use effect,the products have been exported to South Korea, Japan,Pakistan

8,We are a professional supplier, who can provide customers with free product technology, use and other issues

Do you want to find a professional supplier of Gunning Material For Tundish?

Do you want to find a stable and credible supplier?

Then please contact with us

Contact me:

Email:wp@cnjingganrefractory.com/sdwenping@163.com

TEL: 86-0533-4188518 / **FAX:** 86-0533-4188518

Rose:+86-13275332819(wechat/whatsapp number)